

Introduction

Duraglide™ Dry Lubricant is a medical grade, ISO 10993* tested Polytetrafluoroethylene (PTFE) lubricant coating. *Duraglide* Dry Lubricant coatings impart ultra-low surface friction and minimize device actuation problems caused by “stacked tolerances” in low-speed, light-load medical device assemblies. *Duraglide* uses a volatile carrier fluid that quickly deposits a thin, uniform, dry, lubricating PTFE film on any surface geometry. *Duraglide* is suitable for use as-applied, or coated parts may subsequently be thermally treated for improved PTFE adhesion and longer service life.



Product Information

Duraglide Dry Lubricant offers important money saving benefits:

- ISO 10993* tested and certified
- Multiple non-flammable, fast-drying, carrier fluid options
- Long PTFE “hang-time” for excellent coating consistency
- Factory calibrated PTFE content for consistent coating results
- Imparts a low surface coefficient of friction of 0.06
- Simple equipment requirements for high-volume part treatment
- Carrier fluid hostile to bioburden issues
- Compatible with ETO and radiation sterilization processes.
- Non migrating (no silicone)
- Excellent compatibility with metals and plastics
- Minimal solvent odor

Duraglide is available in package sizes from a few ounces up to 55 gallon drums; and also as an aerosol spray. Call *MicroCare Medical* for details on your specific requirements.

Physical & Chemical Properties

| | |
|---|---------------------------------|
| Carrier Odor | Slight Ethereal |
| Coating Odor | None |
| Coating Coefficient of Friction | 0.06 |
| ISO 10993 Tested and Certified | Yes* |
| Solubility in Water | Slight |
| % Volatile by Weight (Carrier) | 100 |
| % Solids by Weight (Typical) | 0.5% - 10.0% |
| PTFE Particle Size Average Bulk Average Mean | 1-15 (microns) 3.7 (microns) |
| Carrier Evaporation Rate (Ether = 1) | >1 |
| Flash Point, Closed Cup (ASTM D 93) Open Cup (ASTM D 1320-86) | Not Flammable Not Flammable |

* Contact *MicroCare Medical* for specifics regarding ISO 10993 certification.

Environmental

All *Duraglide* formulas are accepted by the U.S. Environmental Protection Agency (US EPA) under the Significant New Alternatives Policy (SNAP) program. Contact *MicroCare* for details related to EU REACH compliance requirements.

Duraglide Dry Lubricant formulas are not classified as Hazardous Air Pollutants (HAP) and are not subject to NESHAP regulation. None are SARA Title III Section 313 listed, and none are subject to SARA Title III (EPCRA) reporting requirements.

Biocompatibility

Duraglide Dry Lubricant has been successfully tested to appropriate ISO 10993* protocols. *Duraglide* is not sold for use on permanently implantable devices of any kind. Contact *MicroCare* for full details.

Application Methods

All surfaces should be clean and dry prior to application. Normal precautions (safety glasses, etc.) should be used when moving, dispensing, and using *Duraglide* Dry Lubricant.


Application methods include dipping, wiping, brushing or aerosol sprays. A single application is adequate for most uses.

The most cost-effective dipping process uses a single-ump, vapor degreaser style dipping machine engineered for use with *Duraglide*. This machine puts the carrier fluid into a low-temperature “rolling boil” to insure the PTFE particles remain in suspension without settling. It is a highly reliable means of coating parts while reducing evaporative losses of carrier fluid. Contact *MicroCare* for more details.

Heat Treatment

Heat treatment is not required, but may be used to enhance cosmetics and durability by melting the coating onto the substrate. The process is simple, and involves heating the coated part surface to 305-315 °C (581-600 °F). Maintain the surface temperature of the coated part (not the temperature of the ambient air) at the recommended temperatures for 5 - 10 minutes. The process typically changes the coating appearance from opaque white to translucent and ultimately appears clear and wet. If a white residue remains, buff with a soft cloth after cooling. No further treatment is required.

Packaging and Availability

| Packaging | |
|---|---|
| Liter ¹ - 1 L (Sample Package) 2.5 Lb / 1.13 kg | MCC-XF020L |
| Glass Liter ² - 1 L (Sample Package) 2.5 Lb / 1.13 kg | MCC-XF020GL |
| Steel Gallon ¹ - 1 Gal / 3.79 L 10 Lb / 4.54 kg | MCC-XF020G |
| Steel Pail ¹ - 5 Gal / 18.9 L 50 Lb / 22.68 kg | MCC-XF020P |
| Steel Drum ¹ - 55 Gal / 208 L 500 Lb / 226.8 kg | MCC-XF020D |
| Aerosol ¹ - 14 oz (397 g) | MCC-DGF14A |
| Recycle |  |

Note: Products sold by weight, not volume.

One-gallon and smaller sample containers are available upon request.

The information set forth herein is based on data believed to be reliable. MicroCare makes no warranties express or implied as to its accuracy and assumes no liability arising out of its use by others. This publication is not to be taken as a license to operate under, nor infringe upon, any patents not herein expressly described.



Making Your Devices Better



MicroCare Corporation

595 John Downey Drive
New Britain, CT 06051 USA
CAGE: OATV9
Tel: +1 860 827 0626
Toll Free: 1 800 638 0125
Email: TechSupport@MicroCare.com

MicroCare Europe BVBA

Vekestraat 29 B11
Industriezone 't Sas
1910 Kampenhout, Belgium
Tel: +32 2 251 95 05
Email: EuroSales@MicroCare.com

MicroCare U.K. Ltd

Seven Hills Business Park
Morley
Leeds, West Yorkshire, UK
LS27 8AT
Tel: +44 (0) 113 3501008
Email: mcceurope@microcare.com

MicroCare Asia Pte Ltd

102E Pasir Panjang Road
#03-01 Citilink Warehouse Complex
Singapore 118529
Tel: +65 6271 0182
Email: TechSupport@MicroCare.sg

ISO 9001:2015 Registered

© 2019 MicroCare. All Rights Reserved.

“MicroCare”, “MicroCare Medical”, “Duraglide” and the MicroCare Medical logo are trademarks of MicroCare Corporation.

Rev. 19198

Page 2